



# **TuningFilm 700 BF – Sublime**

## Technical Data Sheet

#### PRODUCT DESCRIPTION

TF 700 BF Sublime is a 85m polymeric stabilized vinyl film coated with a low tack micro-structured acrylic adhesive.

#### **CONSTRUCTION**

#### Face material:

 $85\mu m$  ultra-gloss or matt polymeric stabilized calendered vinyl, cadmium-free.

#### Adhesive:

Repositionable clear solvent based acrylic adhesive.

#### Liner:

Highly stable 145 gsm white micro-embossed PE coated paper.

### TYPICAL USES

TF 700 BF Sublime is designed for Vehicle & Boat Hulls Wrapping (above water line).

The main characteristic of this series is the easiness of application, thanks an excellent repositionability and the Micro-structured adhesive used.

Wrapping has never been so easy!

## **DURABILITY**

Vertical exposure	Zone 1	Zone 2	Zone 3
white & black	8 years	6 years	4 years
colours	7 years	5 years	3.5 years
metallics	6 years	4 years	3 years

Horizontal exposure	Zone 1	Zone 2	Zone 3
white & black	5 years	3.5 years	Not Recom
colours	4 years	3 years	Not Recom
metallics	3.5 years	2.5 years	Not Recom

Boat application: above data reduced by 30%

**Zone 1:** North, West, Central & Eastern Europe, North America (excl. : USA desert's - zone 3)

**Zone 2:** South Europe, Central & South America, Asia Pacific, Australian South coastal area (from Perth to Brisbane), New Zealand

**Zone 3:** Greater Middle East, Africa, Australian Desert areas & North of Perth-Brisbane coastal area, USA (Arizona, California, Florida, Nevada, New Mexico, Texas, Utah), Mexico

#### SHELF LIFE

TF 700 BF - Sublime

2 years stored at 15-25°C and  $\pm$  50 % relative humidity.

#### **PHYSICAL PROPERTIES** (Typical values)

**Thickness** (mm) (Film + adhesive) ISO 543 0.115

Face Material Data, 23°C DIN 53455-5

Tensile strength :> 29 N/15mmElongation at break :> 150 % Adhesive Data, 23°C

FTM 1

Peel adhesion 180° on stainless steel (N/25mm)

- 20 min. residence: 16- 24 hour residence: 18- 1 week residence: 20

Dimensional stability

FTM 14

Shrinkage (48 hours at  $70^{\circ}$ C): < 0.2 %

(25 cm x 25 cm, sample mounted on aluminium).

#### **Temperature ranges:**

Application :  $+15^{\circ}$ C to  $+40^{\circ}$ C End-use :  $-40^{\circ}$ C to  $+90^{\circ}$ C

**Flammability** ISO 3795 Sample mounted on aluminium : self-extinguishing.

#### Solvent and chemical resistance

Resistant to most oils and grease, fuel, aliphatic solvents, weak acids, salts and alkalis.

#### **PROCESSING**

#### Clean and degrease the substrate

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. Use soapy water to remove the dust and degrease with isopropylic alcohol.

## Application

#### on flat or slightly curved surfaces

Apply TF 700 BF Sublime with the dry application method.

#### on convex areas

Heat the film with a heat gun before conforming it over the convex area.

#### on corrugated or concave areas

If the film is stretched into a corrugation it may pop-out after a few weeks.

It is, therefore, recommended to cut the film and to apply it in the corrugation without tension.

# on rivets

Apply the film over the rivet with high pressure and heat it with a heat gun (air temperature over 500°C).

The film may lift slightly after few weeks.

## Application on boat

We recommend edge sealing.

## Removability

Once heated, TF 700 BF Sublime is very easy to remove, leaving almost no adhesive residue on car body.

Some adhesive residue may be expected on gel coat after film removal. Eventual adhesive residues can be removed with isopropylic alcohol.

Removability is warranted only on original manufacturer coating.

## Important remark

Compatibility with paints and lacquers should be tested by the end-user, prior to use.





# **IMPORTANT NOTICE**

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.

All specifications are subject to change without prior notice.